

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
21 July 2005 (21.07.2005)

PCT

(10) International Publication Number  
**WO 2005/067031 A1**

(51) International Patent Classification<sup>7</sup>: **H01L 21/762**,  
41/22, G02B 6/12, G02F 1/39, G11C 11/22

[CH/CH]; Püntstrasse 17, CH-8173 Riedt-Neerach (CH).  
**RABIEI, Payam** [IR/CH]; Hohenklingenstrasse 11,  
CH-8049 Zürich (CH).

(21) International Application Number:  
PCT/CH2004/000365

(74) Agent: **FREI PATENTANWALTSBÜRO**; Postfach  
1771, 8032 Zürich (CH).

(22) International Filing Date: 17 June 2004 (17.06.2004)

(81) Designated States (unless otherwise indicated, for every  
kind of national protection available): AE, AG, AL, AM,  
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,  
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,  
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,  
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,  
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,  
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,  
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,  
ZW.

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
04000408.7 12 January 2004 (12.01.2004) EP

(71) Applicant (for all designated States except US): **EID-  
GENÖSSISCHE TECHNISCHE HOCHSCHULE  
ZÜRICH** [CH/CH]; Rämistrasse 101, CH-8092 Zürich  
(CH).


(84) Designated States (unless otherwise indicated, for every  
kind of regional protection available): ARIPO (BW, GH,  
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,  
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),

(72) Inventors; and

(75) Inventors/Applicants (for US only): **GÜNTER, Peter**

[Continued on next page]

(54) Title: FERROELECTRIC THIN FILMS AND DEVICES COMPRISING THIN FERROELECTRIC FILMS



(57) Abstract: A method of producing a device with a ferroelectric crystal thin film on a first substrate (12) comprises the steps of providing a ferroelectric crystal (1), of irradiating a first surface of said ferroelectric crystal with ions (2) so that a damaged layer (3) is created underneath said first surface, of bonding a block (19) of material including said first substrate (12) to said ferroelectric crystal to create a bonded element (21), wherein an interface is formed between said first surface and a second surface of said block, and of heating the bonded element and separating it at the damaged layer, so that a ferroelectric crystal layer (22) remains supported by the first substrate. By this method, very thin films - down to thicknesses a fraction of a micrometer - of ferroelectric crystals may be fabricated without jeopardizing the monocrystalline structure. According to a preferred embodiment, prior to bonding the block to the second substrate, the first substrate is provided with an electrode layer (13) prior to the bonding. In this way, a thin ferroelectric crystal layer may even be subjected to an applied voltage by electrodes.

WO 2005/067031 A1



European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

**Published:**

— *with international search report*